



Ambitene HTC		
Product	Norm	High density Polyethylene (LDPE)
Characteristics	EN ISO 1133 EN 12099 EN ISO 1183-1 NP EN 15344:2021	Color – Grey MFI – (190°:2,16 kg) (g/10 min) – [0,5;0,8] MFI – (190°:5 kg) (g/10 min) – [1,5;2,5] Residual humidity % Weith loss 105° – <0,20 Density (Kg/m3) – [0,920;0,960] Apparent volumic mass (kg/m3) – [500-600] Filtration – 110 Mycrons
Aplicacions		High quality tube extrusion / Telecommunications / Cable routing.
Description		Developed specially for tube extrusion. To add as a charge, without modify significantly all mechanical materials properties basis.

Review	Data	Technical sheet
02	Fev2022	09